



PRODUCT DATA

## MARC 235 SEALER

Form: liquid

Odor: low

Color: opaque milky white

Specific Gravity: 1.02

Weight per Gallon: 8.5 pounds

Viscosity: low

pH: 8.0 to 8.4

Solids Content: 18%

Crosslinking: zinc

Polymer Type: styrene/acrylic copolymer

Coverage: 700 to 1,500 square feet per gallon

Typical Drying Time: 30 to 45 minutes

Flash Point: none

Strippable: yes

Leveling: excellent

Clarity of Dried Film: excellent

Storage Stability: excellent

Freezability: protect from freezing