

**MARC 261 Slam Dunk** is a one-part water-based urethane/acrylic gym finish with high gloss and high durability in a VOC-compliant low-odor formula. It provides long-term durability and protection with mark resistance for all wooden gym floors.

**Caution:** Contains acrylic and urethane polymers. Avoid eye and skin contact and breathing of vapors. Do not take internally. **IF IN EYES:** Rinse cautiously with water for several minutes. Remove contact lenses if present and easy to do. Continue rinsing. If eye irritation persists, get medical attention. **IF ON SKIN:** Wash with plenty of soap and water. Wash contaminated clothing before reuse. **IF INHALED:** Remove victim to fresh air and keep at rest in a position comfortable for breathing. **IF SWALLOWED:** Rinse mouth with water. Do NOT induce vomiting. Drink plenty of water. Get medical attention. Dispose of in accordance with federal, state and local regulations. Keep container closed with not in use. Do not freeze. Store above 45°.

**KEEP OUT OF REACH OF CHILDREN!**

HMIS/NFPA Ratings: Health = 0, Flammability = 0, Reactivity = 0.

Manufactured in USA from globally sourced materials.

**VOC Content: Under 200 g/l**

Batch Code: \_\_\_\_\_

Expiration Date: \_\_\_\_\_



# SLAM DUNK

## WATER-BASED GYM FINISH



**One-Part Urethane/Acrylic Finish**

- **HIGH GLOSS** •
- **HIGH DURABILITY** •

**Contains Superb Leveling Agents,  
Wetting Agents and Defoamers**

**31% Solids**

**Coverage = 600 to 650 Square Feet per Gallon  
Dry Time = 3 to 24 Hours**

**An Exclusive Formula of M-261**

**MID-AMERICAN RESEARCH CHEMICAL CORP.  
P. O. BOX 927 · COLUMBUS, NE 68602-0927 · 800-228-8508**

### DIRECTIONS

**1. PREPARE FLOOR: NOTE: MARC 261 Slam Dunk Water-Based Gym Finish** is not designed for application to bare wood floors. Use only on previously sealed surfaces.

Scrub and recoat: Dust mop floor and remove all chewing gum and tape. Prepare floor by scuffing with MARC 826 X-Extreme or MARC 827 Gym Conditioning Pads. Tack or autoscrub floor with just water. Perform a final tack with M-831 Trap-It. **NOTE:** Test previously coated floor in an inconspicuous area before recoating to determine compatibility with existing finish. Then apply one or two coats of **MARC 261 Slam Dunk Water-Based Gym Finish** according to the directions below.

**2. APPLY FINISH:** Stir gently before using. Do not thin. Apply **MARC 261 Slam Dunk Water-Based Gym Finish** at a rate of 600 to 650 square feet per gallon. The air and floor temperature should be a minimum of 50°F. Use a heavyweight T-bar applicator with a clean, synthetic pad. When straining finish into a barrel applicator, allow finish to stand for 20 to 30 minutes before applying to floor. This will allow air bubbles to escape. Apply even coats with the grain of the wood while walking at a slow, even pace. Walking too fast may produce excessive bubbling in the finish. Allow a dry time of at least 3 to 24 hours between coats. If the humidity is high (above 70%), allow at least 12 hours between coats. After the first coat has dried, apply a second coat if desired. Do not pour unused finish back into original container.

**3. MAINTAIN DAILY:** Dust mop floor at least daily, or more as required, to keep floor free of dust and dirt. Damp mop spills, salt residue, etc. with MARC 225 Big Bad Orange or MARC 267 Auto Power floor cleaners and a thoroughly wrung out mop.

**4. MAINTAIN WEEKLY:** If soil conditions are heavy, auto-scrub weekly with MARC 818 Blue Soft Autoscrub pads and MARC 225 Big Bad Orange or MARC 267 Auto Power floor cleaners.

**5. RESTORATION:** Dust mop floor. Auto-scrub with MARC 818 Blue Soft Autoscrub pads using MARC 225 Big Bad Orange or MARC 267 Auto Power floor cleaners.

**Net Contents: 5 Gallons**

R0222