

## FEATURES

**MARC 286 Tru-Bond** is a water-based coating which is used to bond new coats of gym finish to existing coatings on the floor. It functions as a tie-coat to help ensure a good bond between the old and new finishes, so that the new finish will not peel or flake off over time. It allows normally incompatible finishes to be used on the same floor.

**MARC 286 Tru-Bond** may also be used to assure a bond between paint lines and gym finish.

**MARC 286 Tru-Bond** works with both oil-based and water-based gym finishes. **MARC 286 Tru-Bond** is non-flammable, and has a mild odor. It is easy to apply with just a mop.

The coverage of **MARC 286 Tru-Bond** is about 1,000 to 2,000 square feet per gallon. Only one coat is required.

**NOTE:** While **MARC 286 Tru-Bond** works with most oil-based and water-based gym finishes, test first if applying over an epoxy-based finish. Do not use over paste waxes.

**KEEP FROM FREEZING!**

HMIS/NFPA Ratings:  
Health-1, Flammability-0, Reactivity-0



# TRU-BOND

## Wood Floor Bonding Coating

Ready-To-Use

Helps Assure Bonding  
of Gym Finishes

Use with Oil-Based  
& Water-Based  
Gym Finishes

Net Contents: 1 Gallon

An Exclusive Formula of

**M-286**

MID-AMERICAN RESEARCH CHEMICAL CORP.  
P.O. BOX 927 COLUMBUS, NE 68602-0927

## DIRECTIONS FOR USE

Sweep gym floor to remove any debris. Screen the gym finish on the floor with MARC 811 100 Grit Sandscreen Discs. Clean floor by damp mopping with clean water, or use an autoscrubber until rinse water remains clear after use. Allow floor to dry completely.

Apply one thin coat of **MARC 286 Tru-Bond** using a rayon finish mop or microfiber flat mop. Coverage should average about 1,000 to 2,000 square feet per gallon. Be sure that all areas of the floor which are to be refinished have been coated with **MARC 286 Tru-Bond**. Any missed spots may result in poor adhesion to the topcoat.

Allow floor to dry for one hour. If the humidity is high (over 70%), additional drying time may be required.

Under normal conditions, apply a coat of gym finish within one to two hours after the **MARC 286 Tru-Bond** has dried.

**CAUTION:** Contains acrylic polymer. May cause eye and skin irritation. Do not contact eyes, skin or clothing. May be harmful if swallowed. If eye or skin contact occurs, flush thoroughly with water for 15 minutes. Get medical attention if irritation persists. Remove and wash contaminated clothing before reuse. If swallowed, do NOT induce vomiting. Drink large amounts of water, and get immediate medical attention. If inhaled, get fresh air.

**KEEP OUT OF REACH OF CHILDREN!**

RU12-12